

First-principles study of the inversion thermodynamics and electronic structure of FeM_2X_4 (thio)spinel ($M = \text{Cr, Mn, Co, Ni}$; $X = \text{O, S}$)

David Santos-Carballal,^{a,*} Alberto Roldan,^{a,b} Ricardo Grau-Crespo,^c Nora H. de Leeuw^{a,b,†}

^a *Department of Chemistry, University College London, 20 Gordon Street, WC1H 0AJ, London, UK*

^b *School of Chemistry, Cardiff University, Main Building, Park Place, Cardiff CF10 3AT, UK*

^c *Department of Chemistry, University of Reading, Whiteknights, RG6 6AD, Reading, UK*

* *E-mail address: david.carballal.10@ucl.ac.uk*

† *Tel.: +44 (0)29 20870658, e-mail address: DeLeeuwN@cardiff.ac.uk*

FeM_2X_4 spinels, where M is a transition metal and X is oxygen or sulfur, are candidate materials for spin filters, one of the key devices in spintronics. We present here a computational study of the inversion thermodynamics and the electronic structure of these (thio)spinel for $M = \text{Cr, Mn, Co, Ni}$, using calculations based on the density functional theory with on-site Hubbard corrections (DFT+ U). The analysis of the configurational free energies shows that different behaviour is expected for the equilibrium cation distributions in these structures: FeCr_2X_4 and FeMn_2S_4 are fully normal, FeNi_2X_4 and FeCo_2S_4 are intermediate, and FeCo_2O_4 and FeMn_2O_4 are fully inverted. We have analyzed the role played by the size of the ions and by the crystal field stabilization effects in determining the equilibrium inversion degree. We also discuss how the electronic and magnetic structure of these spinels is modified by the degree of inversion, assuming that this could be varied from the equilibrium value. We have obtained electronic densities of states for the completely normal and completely inverse cation distribution of each compound. FeCr_2X_4 , FeMn_2X_4 , FeCo_2O_4 and FeNi_2O_4 are half-metals in the ferrimagnetic state

when Fe is in tetrahedral positions. When M is filling the tetrahedral positions, the Cr-containing compounds and FeMn_2O_4 are half-metallic systems, while the Co and Ni spinels are insulators. The Co and Ni sulfide counterparts are metallic for any inversion degree together with the inverse FeMn_2S_4 . Our calculations suggest that the spin filtering properties of the FeM_2X_4 (thio)spinel could be modified via the control of the cation distribution through variations in the synthesis conditions.

PACS number(s): 75.50.Gg, 61.50.Ah, 61.66.Fn

I. INTRODUCTION

The electronics industry has been revolutionized over the last four decades due to the continuous miniaturization of integrated circuits. Spintronics, short for spin electronics, has emerged as the basis for the next generation of electronic devices.¹ The concept of spintronics is to take advantage of both the electron charge and spin in solid-state systems, and therefore its applications require magnetic materials with highly spin-polarized electrons at the Fermi energy.² This can be achieved by half-metallic ferrimagnets (HMF)³ with Curie temperature higher than room temperature. The spin-polarized density of states (DOS) of these compounds has a marked asymmetry around the Fermi energy, where one of the spin channels is a conductor while the other one behaves as an insulator,⁴ making them electronic spin filters. Spintronic applications are based on spin valves,^{5,6} where two HMF layers are sandwiching a non-magnetic layer. In spintronic applications of high efficiency, the resistivity of the spin valve is required to be extremely sensible to the magnetic field (magnetoresistance).¹

The magnetoresistive behavior,^{7,8} and the half-metallic and ferrimagnetic⁹⁻¹² nature of the inverse spinel magnetite (Fe_3O_4), together with the ubiquity of this iron oxide,¹³ indicates its suitability for spintronic applications.^{1,14,15} The origin of these properties in Fe_3O_4 has been traditionally rationalized in terms of its inverse spinel structure. The ferrimagnetism in Fe_3O_4 arises from the

antiparallel alignment of the magnetic moments of the ions in the tetrahedral and octahedral sublattices (which is known as collinear Néel configuration),¹⁶ while the hopping of the extra electron in the minority channel of the spins explains the half-metallic properties.⁹ Greigite (Fe_3S_4) has been shown to have a similar electronic structure to its oxide counterpart Fe_3O_4 .¹⁰ Both compounds are sometimes found associated with other transition metals of similar ionic radii¹⁷ and valence as Fe, such as Mn, Co, Ni and Cr,¹⁸ forming spinel compounds of formula FeM_2X_4 .¹⁹ In these systems, M represents the transition metal and X represents the oxygen or sulfur atom, where the sulfide spinels are usually called thiospinels.²⁰⁻²² The substituted spinels could retain the type of magnetic behavior of their parent compounds (magnetite or greigite), which is driven by a negative superexchange interaction that is stronger between ions occupying different sublattices than between ions within the same sublattice.¹⁶

The crystal structure of a (thio)spinel is face-centered-cubic and the space group is $Fd\bar{3}m$. The cubic unit cell contains eight units of FeM_2X_4 where the 32 anions are in a cubic closed packed arrangement, while 8 of the tetrahedral sites and 16 of the octahedral ones are occupied by all the cations, see Fig. 1. As originally suggested by Barth and Posnjak,²³ different cation arrangements of the (thio)spinel formula can be rewritten as $(\text{Fe}_{1-x}\text{M}_x)_\text{A}(\text{Fe}_x\text{M}_{2-x})_\text{B}\text{X}_4$, where A and B denote tetrahedral and octahedral sites respectively, while x is the degree of inversion. In normal spinels ($x = 0$), Fe ions occupy exclusively the A sublattice and M is confined to the B sublattice. In inverse spinels ($x = 1$), the A sublattice holds half of the M cations and the B sublattice is equally populated with Fe and M ions. When $0 < x < 1$, Fe and M have an intermediate degree of distribution within the A and B sublattices. For all inversion degrees, the $Fd\bar{3}m$ symmetry of the spinel is usually retained, as long as all cations are distributed completely randomly within each sublattice, which makes all the sites within each sublattice effectively equivalent. In such cases the cation distribution is fully characterized by the inversion degree x . The degree of inversion in spinels has been found to be affected by different factors, including the ionic radii of

the distributed species, the electronic configuration, the electrostatic energy of the lattice, the short-range Born repulsion energy, crystal field effects, and polarization effects.^{18,19}




FIG. 1. Schematic representation of one full unit cell of a perfect spinel, highlighting one of the four primitive rhombohedral cells. The spinel structure has the symmetry group $Fd\bar{3}m$ with three ion sites: tetrahedral (A), octahedral (B) cation positions and the anion (X) position.

Structural aspects of FeM_2X_4 (thio)spinel have been reported extensively in the literature, sometimes also addressing their influence on the magnetic and electronic properties. For example, these studies include: (1) the mixing, non-stoichiometry²⁴ and magnetic properties as a function of the cation site distribution of the Fe_3O_4 - $FeCr_2O_4$ system;²⁵ (2) the magnetic ordering of $FeCr_2O_4$ ²⁶⁻²⁹ and $FeMn_2O_4$ ³⁰ upon crystal symmetry lowering; (3) the relevance of the electronic structure to the magnetic properties of $FeCr_2X_4$;³¹ (4) the transport properties based on the half-metallic electronic structure of $FeCr_2S_4$;³² (5) the magnetic structures in $FeCr_2X_4$ ³³ and the colossal magnetoresistance in $FeCr_2S_4$;³⁴ (6) the degree of inversion in $FeMn_2O_4$ ³⁵⁻³⁸ and $FeCo_2O_4$;³⁹⁻⁴¹ (7) the structural phase stability and magnetism in $FeCo_2O_4$;⁴² (8) the structural and magnetic properties of $FeNi_2O_4$;⁴³ as well as (9) the thermodynamic stability⁴⁴ and cation distribution of $FeNi_2S_4$.^{45,46} Nevertheless, in compounds such as these (thio)spinel, where the other transition metal's atomic number differs only by 1 from Fe, the X-ray diffraction intensities

are very similar for any inversion degree, which makes it difficult experimentally to differentiate the location of the cations in the structure.

Owing to the experimental limitations for the determination of the cation arrangement in FeM_2X_4 (thio)spinel, in the present work we have used DFT+ U calculations to investigate systematically how modifying the spinel composition affects the equilibrium inversion degree and how this determines the magnetic and electronic properties at a given composition. We study the influence of the nature of the M and X ions ($M = \text{Cr, Mn, Co, Ni}$ and $X = \text{O, S}$) on these properties, a type of investigation that has been undertaken previously for other groups of oxide spinels¹⁴ and Heusler alloys^{47,48} with potential application in spintronic devices. We will discuss from a thermodynamic point of view the equilibrium cation distribution of these (thio)spinel and the role of the ions' sizes and crystal field stabilization effects. We will also analyze the dependence of the electronic and magnetic structure on the degree of inversion for the normal and completely inverse systems.

II. COMPUTATIONAL METHODS

A. Calculation details

We have carried out spin-polarized quantum mechanical calculations using density functional theory (DFT) as implemented in the Vienna *Ab-initio* Simulation Package (VASP).⁴⁹⁻⁵² The Perdew-Burke-Ernzerhof functional revised for solids (PBEsol)⁵³ was the version of the generalized gradient approximation (GGA) used as exchange-correlation functional for all geometry optimizations and for the calculation of all density of states (DOS), because PBEsol provides a better description of the structure of solids than its parent functional.⁵⁴

The semiempirical method of Grimme (D2) was also included in our calculations for modelling the long-range van der Waals interactions.⁵⁵ Even when these interactions are not expected to affect significantly the bulk properties of the hard solids investigated here, we have included the

D2 correction at this stage because in future work we expect to study the surfaces of these solids and their interactions with adsorbates, where dispersion effects may play a significant role.^{56–61} The projector augmented wave (PAW) pseudopotential method^{62,63} was used to describe the core electrons and their interaction with the valence electrons, *i.e.* those in level $4d$ for Fe, Co and Ni, $3p4d$ for Cr and Mn, $2s2p$ for O and $3s3p$ for S. The kinetic energy cutoff for the plane-wave basis set expansion was set at 520 eV for the geometry optimizations in order to avoid the Pulay stress arising from the cell shape relaxations. A Monkhorst-Pack grid of $7 \times 7 \times 7$ Γ -centred k -points^{64–66} was used for all calculations. During relaxation, Feynman forces on each atom were minimized until they were less than $0.01 \text{ eV} \cdot \text{\AA}^{-1}$. For the calculation of the DOS we applied the tetrahedral method with Blöchl corrections. Atomic charges and atomic spin moments were analyzed using the Bader partition methodology⁶⁷ in the implementation of Henkelman *et al.*^{68–70}

In order to improve the description of the highly correlated $3d$ electrons in the spinels under study, we have included the Dudarev *et al.*⁷¹ approach for the d orbital correction within the DFT + U method.⁷² We report in Table I the values used for the on-site Coulomb interaction term of d Fe and d M. These values were determined by fitting the calculated positions of the d band centers to those obtained from calculations using the screened hybrid functional of Heyd-Scuseria-Ernzerhof (HSE06),^{73–79} which provides band gaps of better quality than semi-local functionals.⁸⁰ The HSE06 is made up from the Perdew-Burke-Ernzerhof functional (PBE)^{81,82} exchange and correlation components, mixed with 25% of short-range Hartree-Fock (HF) exchange.⁷³ The Coulomb potential exchange is replaced by a screened potential (with screening parameter $\omega = 0.207 \text{ \AA}^{-1}$) in order to define the separation between the short- and long-range components of the HF exchange.⁷⁹ While the amount of short-range HF is a constant determined by perturbation theory, making HSE06 an adiabatic connection functional in this part of the potential,⁸³ its screening parameter is a reasonable system-averaged value across a

wide variety of systems, giving better agreement with experiments in the case of semiconductors than for metals or insulators.⁸⁰

For the fitting, we carried out single-point calculations with both PBEsol + U and HSE06, using unrelaxed structures with normal cation distributions (a_0 and u_0 were taken from experiment for these calculations, values are listed in Table II). In a first step, we determine U_{eff} for Fe, by considering the Fe_3O_4 and Fe_3S_4 electronic structures (which have been studied before).^{10,44,84} We then keep these values for Fe and perform a set of DFT + U calculations where the effective Hubbard parameter (U_{eff}) of the M ion was changed in steps of 0.5 eV from 0 to 6.0 eV. In all the HSE06 calculations, we used the same settings as for the PBEsol simulations.

TABLE I. Summary of the optimum effective Hubbard parameter (U_{eff}) in eV used through this work for the spinel oxides and sulfides.

	Cr	Mn	Fe	Co	Ni
FeM_2O_4	4.0	3.5	4.0	1.5	5.5
FeM_2S_4	2.0	2.5	3.5	0.5	4.5

We found that the optimum U_{eff} values for the Cr, Mn and Fe ions in the spinel oxides are within 0.5 eV of the ones previously found for PBE + U by Wang *et al.*⁸⁵ via comparison of experimental and theoretical formation energies of metal oxides. The two exceptions are the U_{eff} values for Co and Ni which differ, according to our methodology, by 1.8 and 0.9 eV respectively from the ones reported by Wang *et al.*⁸⁵ The smaller U_{eff} values of the thiospinels, compared to their oxide counterparts, reflect their more covalent character. The U_{eff} for Mn-based thiospinel compares well with the value reported by Rohrbach *et al.*,⁸⁶ while, according to our methodology, the one for Fe is 1.5 eV above the one used by the same authors. Hence, in general our U_{eff} are similar to previously employed values, with some differences which can be expected from the use of a different starting functional (PBEsol in our case), implementation of the method, different compound or different fitting procedure.

All the calculations were performed in the rhombohedral primitive unit cell of the FeM_2X_4 spinels, which comprises 14 atoms, see Fig. 1. For each composition of $(\text{Fe}_{1-x}\text{M}_x)_\text{A}(\text{Fe}_x\text{M}_{2-x})_\text{B}\text{X}_4$, we considered three values of x (0, 0.5 and 1.0). When using this cell, the site occupancy artificially lowers the symmetry from space group $Fd\bar{3}m$ (No. 227) in the normal spinel to $R\bar{3}m$ (No. 160) in the half-inverted and to $Im\bar{m}a$ (No. 74) in the fully-inverted spinel.⁸⁷ The use of the primitive cell ensures that there is a single cation configuration for each of these three degrees of inversion, which simplifies the simulations, allowing us to scan a wide range of FeM_2X_4 compositions. This approximation follows previous work, where the use of the primitive cell model has been found to adequately describe experimental properties of half- and fully-inverted spinels.⁸⁷⁻⁹¹ However, we cannot rule out completely that the use of larger supercells could actually lead to cation configurations with lower energies for the same inversion degree, as found for example in a recent study of CoFe_2O_4 .⁹²

Following the collinear Néel model, the initial magnetic moments of the atoms within each sublattice were set parallel among themselves and antiparallel to those of the other sublattice. For each inversion degree, we ran several calculations, specifying different initial magnetic moments, corresponding to different combinations of low- and high-spin states for the transition metal ions in each sublattice, in order to identify the ground state. The magnetic moments were allowed to relax during each of the calculations. It should be noted that the magnetic structure with antiparallel sublattices is not strictly valid in the case of FeCr_2O_4 , which is known to have a spiral magnetic structure.³³ However, for the sake of comparison with the other spinel systems, we have not considered its different magnetic structure in this study.

The experimental lattice (a_0) and anion (u_0) parameters (defining the anion position in the crystal) of the spinels are shown on Table II. These were used as the starting structures for our simulations, where a_0 and the internal coordinates were allowed to relax fully for each inversion degree. We kept the cell shape perfectly rhombohedral in such a way that the conventional cell

was always cubic. As FeMn_2S_4 and FeCo_2S_4 spinels have not been characterized so far, we postulated an initial hypothetical structure for both. For the Mn- and Co-based thiospinels, we kept the same initial anion parameter as in their oxide counterparts and scaled up their initial lattice parameter according to the equation:

$$a_0(\text{FeM}_2\text{S}_4) = \frac{a_0(\text{Fe}_3\text{S}_4) \cdot a_0(\text{FeM}_2\text{O}_4)}{a_0(\text{Fe}_3\text{O}_4)}, \quad (1)$$

which gives the estimates shown in Table II.

TABLE II. Summary of the initial unit cell lattice (a_0) and anion (u_0) parameters of FeM_2X_4 spinels used in this work. The relaxed a and u are also reported for $x = 0, 0.5$ and 1 . Note that the origin is the center of symmetry.¹⁹

Structure	Experimental			$x = 0$		$x = 0.5$		$x = 1$	
	a_0 (Å)	u_0	Reference	a (Å)	u	a (Å)	u	a (Å)	u
FeCr_2O_4	8.38	0.261	33	8.351	0.261	8.372	0.261	8.392	0.265
FeCr_2S_4	10.00	0.259	33	9.830	0.258	9.855	0.262	9.898	0.260
FeMn_2O_4	8.51	0.250	93	8.420	0.256	8.436	0.265	8.446	0.267
FeMn_2S_4	10.04	0.250	This paper*	9.911	0.255	9.949	0.260	9.983	0.263
Fe_3O_4	8.390	0.255	94	--	--	--	--	--	--
Fe_3S_4	9.88	0.251	95	--	--	--	--	--	--
FeCo_2O_4	8.24	0.259	40	8.196	0.256	8.168	0.259	8.119	0.271
FeCo_2S_4	9.73	0.259	This paper*	9.363	0.263	9.286	0.260	9.297	0.250
FeNi_2O_4	8.29	0.258	43	8.124	0.259	8.123	0.260	8.133	0.255
FeNi_2S_4	9.47	0.257	45	9.463	0.260	9.438	0.257	9.396	0.251

* Experimental information is not available. Parameters are obtained by scaling the values for the corresponding oxides.

B. Configurational free energy of inversion

The calculation of the inversion degree in spinels containing two different cations is based on the thermodynamic considerations of Navrotsky and Keppla,⁹⁶ which have proved to agree well with experiments.^{88,97-100} This methodology is based on the treatment of the spinels' cation distribution as a chemical equilibrium. We calculated the configurational free energy of inversion per formula unit ΔF_{config} as,

$$\Delta F_{\text{config}} = \Delta E_{\text{config}} - T \cdot \Delta S_{\text{config}}, \quad (2)$$

where ΔE_{config} is the inversion energy per formula unit, T is the temperature and ΔS_{config} is the ideal configurational entropy also per formula unit, which is calculated as,

$$\Delta S_{\text{config}} = -R \left[x \ln x + (1-x) \ln(1-x) + x \ln \frac{x}{2} + (2-x) \ln \left(1 - \frac{x}{2} \right) \right], \quad (3)$$

where R is the ideal gas constant. $\Delta S_{\text{config}} = 0$ and $11.59 \text{ J}\cdot\text{mol}^{-1}\cdot\text{K}^{-1}$ for $x = 0$ and 1 respectively, while it reaches the maximum value $15.88 \text{ J}\cdot\text{mol}^{-1}\cdot\text{K}^{-1}$ for the complete random distribution at $x = 2/3$. The above expression means that we have only considered ideal contributions to the configurational entropy, in line with previous work.^{88,97,100} We are also ignoring vibrational contributions to ΔF , as their contributions are typically small compared to configurational energies and entropies.^{88,100}

III. RESULTS AND DISCUSSION

A. Equilibrium structures

Table II shows the optimized a and u for the three inversion degrees considered ($x = 0, 0.5$ and 1.0). In general, the optimized lattice parameter is within 2% from the experimental value, where this is available. However, the relaxed lattice parameter for FeCo_2S_4 , in the best case ($x = 0$), is 3.8% away from the initial estimated value, which may be an artefact due to the assumption of linearity between the lattice constants of Fe_3O_4 , FeCo_2O_4 and their sulfide counterparts. After relaxation of the structures, u was still different from the value of $1/4$ that it has in the perfect spinel. This deviation reflects the displacement, in the (111) direction, of the anion from its ideal position in order to accommodate cations of specific volume. The biggest deviation in u in comparison with the experimental value was for the inverse Mn- and Co-based oxide spinels, Table II. We see that in general, u and a values are sensitive to the cation distribution, although no systematic rule can be derived from their dependence.

B. Equilibrium inversion degrees

The configurational inversion energy per formula unit (ΔE_{config}) was fitted *versus* the degree of inversion (x) using a quadratic regression curve, see Fig. 2 (a). More details regarding the empirical relationship¹⁰¹ and theoretical justification¹⁰² of the above fitting in terms of x , a and u can be found elsewhere. In this fitting, we defined the normal spinel as the standard state for a given condition of temperature and pressure.

Using the quadratic equation for ΔE_{config} , it is possible to interpolate the inversion energy for any value of x between 0 and 1. Based on this protocol, we have also estimated the configurational free energy of inversion for a typical firing temperature of 1000 K^{31,42,43,45} (among the known cases in this study, FeNi₂S₄ is an exception, as it is usually prepared at 573 K^{45,103} because it decomposes at 734 K¹⁰⁴) by using equations (2) and (3). Compounds are usually quenched after synthesis at the firing temperature, retaining the equilibrium cation distribution. We analysed the ΔE_{config} dependence with x and provided the equilibrium values of x , *i.e.* the ones that satisfy $\partial F_{\text{config}}/\partial x = 0$ at 1000 K, see Fig. 2 (b).




FIG. 2. (a) Configurational inversion energy (ΔE_{config}) and (b) configurational inversion free energy (ΔF_{config}) as a function of the inversion degree for FeM_2X_4 spinels. Inset shows enlargement of ΔF_{config} for the FeMn_2X_4 and FeNi_2X_4 (thio)spinels.

We found the minimum of ΔE_{config} to correspond to a normal distribution of cations, with the exception of Co-based systems and FeMn_2O_4 , Fig. 2 (a). The lowest value of ΔE_{config} for FeCo_2O_4 spinel is found to be an inverse cation distribution, whereas for FeMn_2O_4 , both normal and inverse cation distribution structures lie at similar energies, while the intermediate degree of inversion ($x = 0.5$) is only ~ 14 kJ·mol⁻¹ above the ground state. FeCo_2S_4 is an atypical thiospinel in this study, in the sense that it shows a critical point of low energy with intermediate cation distribution, at $x = 0.53$.

FeCr_2X_4 . From Fig. 2 (b), we deduced that at 1000 K, the Cr-based (thio)spinels are normal under equilibrium conditions, as a result of a highly endothermic process of inversion. This

normal cation distribution of FeCr_2X_4 is supported by powder neutron diffraction intensities³³ at room temperature and for the oxide by Mössbauer measurements²⁵ and DFT calculations,²⁴ see Table III.

TABLE III. Summary of equilibrium inversion degree (x) of FeM_2X_4 (thio)spinel from this work and previous reports.

	x	Reference	x at 1000 K
FeCr_2O_4	~ 0.0	24,33	0.00
	0.00	25	
FeCr_2S_4	~ 0.0	33	0.00
FeMn_2O_4	0.5	35,36	0.10 and 1.00
	0.91	37,38	
$\text{FeMn}_2\text{S}_4^*$	--	--	0.03
FeCo_2O_4	0.52	105	1.00
	0.54	40	
	0.565	39	
	0.605	106	
	0.7	107	
	1.0	108,109	
$\text{FeCo}_2\text{S}_4^*$	--	--	0.48
$\text{FeNi}_2\text{O}_4^*$	--	--	0.25
FeNi_2S_4	~ 0.05	110	0.12
	0.82 or 1.00	21	
	1.00	22,45,46	

* Experimental information is not available.

FeMn_2X_4 . At 1000 K, the scenario for FeMn_2O_4 is unique in this study, as in addition to the global minimum of ΔF_{config} at $x = 1$, it has a local one at $x = 0.1$. The local minimum is within a portion of shallow inversion free energy ($0 < x < 0.3$), which may lead to a metastable inversion degree anywhere within this range, for this spinel's equilibrium structure, see Fig. 2 (b). The behaviour of this thermodynamic property in FeMn_2O_4 can be rationalized in terms of the small change of ΔE_{config} with x as well as in $E_{x=0} \approx E_{x=1}$. The upper limit ($x = 0.3$) of the shallow inversion free energy that we predicted agrees semiquantitatively with the experimental inversion degree ($x = 0.5$) found for FeMn_2O_4 in a conductivity and thermopower³⁵ investigation, as well as inferred from the study of a series of spinels,³⁶ see Table III. The inversion degree has also been found in neutron diffraction experiments to be at $x = 0.91$ ^{37,38} which is in reasonably good agreement with the global minimum calculated here. We speculate that the two inversion degrees

of FeMn_2O_4 may be hampered by kinetic control, a situation that is outside the scope of this paper, but which explains the different cation arrangements described in the literature. According to our calculations, samples of FeMn_2O_4 synthesized above 1150 K can only have inverse cation distribution, as the metastable inversion degree vanishes. FeMn_2S_4 , on the other hand, is predicted to be mostly normal ($x = 0.03$) under equilibrium conditions, Fig. 2 (b).

FeCo₂X₄. FeCo_2O_4 is the only completely inverse spinel under equilibrium conditions, due to the highly exothermic process of inversion, which agrees with experimental evidence.^{108,109} Nevertheless, our results for the Co-based oxide disagree with the equilibrium inversion degree of $x = 0.565$ and 0.605 obtained by means of fitting the dependence of the magnetic moment with x ^{39,106} and the similar values within the range $0.52 \leq x \leq 0.7$ derived from Mössbauer spectra,^{40,105,107} see Table III. Its sulfide counterpart, which has not been studied experimentally, shows an equilibrium inversion degree of $x = 0.48$ in our calculations.

FeNi₂X₄. FeNi_2O_4 (and to a lesser extent FeNi_2S_4) is predicted to have an intermediate distribution of the cations under equilibrium conditions of around $x = 0.25$ ($x = 0.12$ for the thiospinel case). Our results agree with suggestions of partially inverted FeNi_2S_4 , based on a high temperature calorimetry study of natural samples,¹¹⁰ see Table III. However, they disagree with the more recent description of synthetic FeNi_2S_4 samples as completely inverse spinel based on a neutron powder diffraction measurements at temperatures between 100 and 573 K,⁴⁵ thermodynamic-based modelling,⁴⁶ EXAFS experiment²² and Mössbauer data.²¹ Based on our calculations and the fact that synthetic FeNi_2S_4 samples cannot be annealed to temperatures higher than 734 K,¹⁰⁴ as they decompose, we propose a rationalization of the different cation arrangements found in natural and synthetic samples of this mineral. We suggest that synthesis produces a kinetic product (with $x \sim 1.00$) and that these conditions cannot reproduce the hypogene processes occurring in the ores deep below the Earth's surface that lead to the thermodynamic product found in natural samples ($x \sim 0$).

C. Size of ions and crystal field stabilization effects

We analyze now the effect of cation size and crystal field stabilization energy on the distribution of cations under equilibrium conditions.

Assuming the hard-sphere model, where the ions are spherical, rigid and in contact, the ratio between the tetrahedral (R_A) and octahedral (R_B) bond distances will depend solely on u . The tetrahedral holes are smaller than the octahedral ones for $u < 0.2625$.¹¹¹ Taking into account that for most systems under study here, u is below that value (with a few exceptions in the relaxed structures, see Table II), we can consider that $R_A < R_B$ is expected for a stable spinel.

According to the Shannon effective radii,¹⁷ which depend on the coordination number and oxidation state, Fe_A^{2+} cation has bigger radius than Cr_B^{3+} , Co_B^{3+} and Ni_B^{3+} leading to an inverse cation distribution. This agrees very well with our thermodynamic DFT + U calculations for FeCo_2O_4 and moderately with the partially inverse ($x = 0.48$) FeCo_2S_4 spinel. However, we found the opposite equilibrium distribution for the FeCr_2X_4 system and a very small inversion degree ($x < 0.25$) for the FeNi_2X_4 , indicating that this factor is not the key parameter governing the inversion degree in these compounds. On the other hand, the Mn_B^{3+} Shannon radius is bigger than that of Fe_A^{2+} , predicting a normal (thio)spinel. Yet, whereas the sulfide compound is a completely normal spinel, the oxide has a local minimum for $0 < x < 0.3$ and the global one at $x = 1$.

Since we are dealing with open shell d transition metals, the crystal field is also an important effect to consider. McClure,¹¹² and independently Dunitz and Orgel,¹¹³ derived the crystal field stabilization energy for ions (in oxides) with tetrahedral and octahedral environments, to estimate the relative stability of normal and inverse spinels. Subtracting the tetrahedral stabilization energy from the octahedral one (octahedral site preference energy – OSPE) gives an idea of the octahedral site preference. The OSPE for Fe^{2+} (16.3 kJ/mol) is smaller than for the rest of the

cations under consideration here, *i.e.* 195.4 kJ/mol for Cr^{3+} , 105.9 kJ/mol for Mn^{3+} , 79.5 kJ/mol for Co^{3+} and 95.4 kJ/mol for Ni^{2+} (note that to date no estimation of OSPE for Ni^{3+} is reported). These OSPEs clearly show the preference for normal spinels.

The ambiguities in our results are probably not surprising, because earlier attempts to correlate cation distribution with their size and crystal field effects were also not successful, or at least, unable to provide a complete prediction of the degrees of inversion.¹¹⁴

D. Atomic spin moments and charges

In this and the next section we analyze the electronic and magnetic properties of the spinel materials for the extreme cases of $x = 0$ and $x = 1$.

The total magnetization of saturation (M_s) is defined experimentally as the maximum magnetic moment per formula unit of a compound under an increasing magnetic field. This magnitude can also be calculated according to the Néel model as the sum of the atomic spin densities (m_s) in the tetrahedral and octahedral sublattices per formula unit.¹⁶ Table IV shows the atomic spin densities for all the compounds under study here. When $x = 0$ in the oxide spinels, $m_s(\text{Fe}_A)$ is around $4 \mu_B/\text{atom}$, which is in good agreement with a high-spin electronic distribution for $\text{Fe}_A^{2+} : e_{\uparrow}^2 e_{\downarrow}^1 t_{\uparrow}^3$, with the exception of the deviation in the Cr-based compound. For the normal thiospinels there is more consistency in the $m_s(\text{Fe}_A)$ values, as they lie in the range -3.41 and $-3.53 \mu_B/\text{atom}$ and only in semiquantitative agreement with the Néel model. For the M cation in the normal Cr- and Mn-based (thio)spinels, the atomic spin densities are also in good agreement with high-spin electronic distributions. We found that our DFT+ U calculations underestimated the atomic spin moment of FeCo_2O_4 (when $x = 0$) by $1.28 \mu_B/\text{atom}$ compared with the one expected from the Néel model for the high-spin distribution of $\text{Co}_B^{3+} : t_{2g\uparrow}^3 t_{2g\downarrow}^1 e_g^2$. In its sulfide counterpart with normal distribution, our calculated value compares well with the one predicted from a low-spin distribution of Co_B^{3+} , which renders the ions as non-magnetic. In the case of

Ni_B^{3+} , we also found it to be low spin $t_{2g}^3 \uparrow t_{2g}^3 \downarrow e_g^1 \uparrow$, although our results overestimated by 0.39 μ_B/atom and underestimated by 0.10 μ_B/atom the expected value for the oxide and sulfide respectively. This agrees with the low-spin cation occupying the octahedral positions in violarite, interpreted previously as Fe^{2+} .²¹

TABLE IV. Atomic spin density per atom (m_s) and total spin magnetization of saturation per formula unit (M_s) both calculated by means of a Bader analysis and in μ_B .

Spinel	x	m_s					M_s	m_s					M_s
		A	B1	B2	$X = \text{O}$	A		B1	B2	$X = \text{S}$			
FeCr_2X_4	0	-3.72	2.92	--	-0.03	2.00	-3.46	2.95	--	-0.11	2.00		
FeCr_2X_4	1	-3.50	2.82	4.09	0.15	4.00	-3.28	2.86	3.79	0.16	4.00		
FeMn_2X_4	0	-3.97	4.16	--	-0.09	4.00	-3.53	4.03	--	-0.13	4.00		
FeMn_2X_4	1	-4.49	3.73	4.17	0.15	4.00	-4.17	3.94	3.84	0.10	4.02		
FeCo_2X_4	0	-3.95	2.72	--	0.13	2.00	-3.45	-0.04	--	-0.08	-3.87		
FeCo_2X_4	1	-2.44	0.01	4.11	0.08	2.00	-0.91	0.03	3.32	0.00	2.46		
FeNi_2X_4	0	-4.04	1.39	--	-0.18	-2.00	-3.41	0.90	--	-0.02	-1.69		
FeNi_2X_4	1	-1.89	1.59	4.10	0.05	4.00	-0.52	0.86	3.50	0.04	4.00		

In the inverse (thio)spinel, the calculated spin densities for Fe_{B2}^{2+} were slightly overestimated in the oxides compared with the Néel model, while they were more moderately underestimated in the sulfides considering a high-spin electronic distribution of $t_{2g}^3 \uparrow t_{2g}^1 \downarrow e_g^2 \uparrow$ for these ions, see Table IV. The calculated atomic spin densities of the inverse Cr- and Mn-based (thio)spinel agree better, especially in the cations occupying the octahedral (B1) positions, with the high-spin electronic distribution for these ions, as described for the normal spinels. However, in the Co- and Ni-based inverse compounds, we found low-spin densities for these atoms in the B1 positions, where the nearly diamagnetic Co_{B1} in the inverse FeCo_2O_4 agrees with experiments.^{108,109} Notable exceptions are the Co_A^{3+} in the thiospinel and Ni_A^{3+} in both oxide and sulfide compounds, where our calculations shift m_s by more than 1 μ_B/atom with the expected value (in the best case) from a low-spin electronic distribution for these atoms.

The most stable normal cation distribution of FeCr_2O_4 gave the closest M_s to the experimental one, although still overestimated by 1.35 $\mu_B/\text{f.u.}$, as this measurement was carried out at a

temperature in which the spins are not collinear anymore.³³ In the case of its normal sulfide counterpart, the difference in spin magnetization of saturation with the experiments is smaller ($0.41 \mu_B/\text{f.u.}$).³³

The Ni-based (thio)spinel are found experimentally to be paramagnetic.^{21,43,103} In the oxide this has been explained as being due to high-spin Fe^{3+} ions exclusively localized on the A sublattice whose spins compensate completely the $[\text{Ni}^{2+}\text{Ni}^{3+}]$ occupying the octahedral positions.⁴³ In the sulfide this has been rationalized on the basis of an A sublattice filled by Ni^{3+} and low-spin Fe^{2+} occupying octahedral positions.²¹ Here, based on our calculated spin magnetization of saturation and assuming intermediate degrees of cation distribution, we present a fresh explanation for the paramagnetism of FeNi_2X_4 . Considering that M_s changes linearly with x , we may postulate that the oxide and sulfide will be paramagnetic when $x = 0.33$ and 0.30 respectively. Although this suggestion agrees with the oxide and sulfide equilibrium inversion degree calculated in section 3.1, it shows that paramagnetism in these compounds may be due not to the canonical inverse spinel structure with integer oxidation numbers, but to intermediate inversion degrees.

To the best of our knowledge, there is no experimental determination of the saturation magnetization of either FeCo_2S_4 or FeMn_2S_4 . Although we found both compounds to be ferrimagnetic, the measurement of M_s for FeCo_2S_4 may be essential to determine the inversion degree of this spinel, as our calculation of the normal and inverse cation distributions show different magnetizations of saturation. Our results agree with the ferrimagnetic behaviour described for FeCo_2O_4 ¹¹⁵ and FeMn_2O_4 ,³⁰ below the Curie (Néel) temperature.

Table V shows the charges (q) gained or lost by an atom with respect to the neutral atom in the FeM_2X_4 spinels. We clearly appreciate, that charges are systematically underestimated for all the FeM_2X_4 (thio)spinel. For the Cr- and Mn-based (thio)spinel, q_A is clearly smaller than q_B for any inversion degree and also for the inverse FeCo_2O_4 . However, for the Co- and Ni-based systems, the relative charges of the atoms in the tetrahedral and octahedral positions is different in the

oxide and sulfide. In the spinel oxides, together with the normal Co- and Ni- thiospinels, q_A is bigger than q_B , while in the inverse thiospinels, it is the other way round.

TABLE V. Calculated Bader charges in the FeM_2X_4 spinels.

Spinel	x	A	B1	B2	$X = O$	A	B1	B2	$X = S$
$FeCr_2X_4$	0	1.33	1.75	--	-1.21	0.92	1.22	--	-0.84
$FeCr_2X_4$	1	1.47	1.76	1.58	-1.20	1.11	1.22	1.12	-0.86
$FeMn_2X_4$	0	1.50	1.56	--	-1.16	0.95	1.18	--	-0.83
$FeMn_2X_4$	1	1.41	1.69	1.68	-1.20	1.08	1.21	1.17	-0.86
$FeCo_2X_4$	0	1.52	1.34	--	-1.05	0.86	0.54	--	-0.49
$FeCo_2X_4$	1	1.30	1.31	1.68	-1.07	0.46	0.60	0.95	-0.50
$FeNi_2X_4$	0	1.61	1.18	--	-0.99	0.86	0.57	--	-0.50
$FeNi_2X_4$	1	1.27	1.16	1.67	-1.03	0.26	0.61	0.99	-0.46

E. Electronic density of states

1. $FeCr_2X_4$

The density of states (DOS) in Fig. 3 show that at $x = 0$, $FeCr_2X_4$ is half-metallic, which we confirmed by the integer value of total spin magnetization ($M_S = 2.00 \mu_B/\text{f.u.}$), see Table IV. An integer value of the total spin magnetization discriminates half-metals and insulators from metals. The total number of electrons of any stoichiometric system is integer (n) and if it has a band gap at least in one spin channel, there is an integer number of electrons (n') there too. This makes the difference ($n'' = n - n'$), which is the number of electrons on the band that crosses the Fermi level also integer. Therefore, the magnetization of saturation, *i.e.* the difference of n' and n'' , is also integer.^{3,15,116,117}

The DOS shows a sharp peak of the partially-occupied e level of Fe_A ions in the majority spin channel (α) crossing the Fermi energy, which is weakly hybridized with the empty Cr e_g level in the oxide spinel, while the minority spin channel (β) shows a gap near E_F . There is a nearly equally intense band due to the occupied $Cr_B t_{2g}$ level in the majority channel of the spins at -3.0 eV in the oxide (-1.75 eV in the sulfide), which suggests that the half-metallic properties do not involve the sublattice B. In the oxide, the other valence bands of the Fe_A ions (t_2 and e levels)

appear in the minority channel of the spins below -2.5 eV, always strongly hybridized with the O $2p$ orbitals. However, the Cr t_{2g} level, together with a small contribution from the e_g orbitals, in the valence part of the majority spin channel are weakly hybridized with the O $2p$ orbitals. The unoccupied t_2 level of Fe_A appears at 3.0 eV in the majority channel of the spins while Cr_B has the unoccupied t_{2g} level in the majority channel of the spins (1.5 eV) and the t_{2g} and e_g levels in the minority channel of the spins (2.5 and 4.0 eV).

The inversion of half of the Cr cations to the tetrahedral positions in $FeCr_2X_4$, generates four non-equivalent types of atoms (B1 and B2 are the two types of atoms occupying B positions), see Fig. 3 right panels. With this cation distribution, the (thio)spinel is still half-metallic ($M_S = 4.00 \mu_B/\text{f.u.}$, see Table IV), but unlike in the normal spinel structure, through the minority channel of the spins due to the partially-occupied t_2 level of the Cr_A ions. All the Cr_A bands are shifted towards higher energy values with respect to Fe_A in the normal (thio)spinel. The Cr_{B1} d bands appear roughly in the same position as in the normal (thio)spinel, although less intense. The e_g and t_{2g} levels of Fe_{B2} , which lie very close or are hybridized, are around -8.0 and 1.5 eV in the α and β channel of the spins, respectively. As a result of the cations' shifted and split bands, there is less hybridization of the O $2p$ orbitals in the valence regions compared to the normal spinel, which are prominent in this section. The main difference, for any cation distribution, between the DOS of $FeCr_2S_4$ and its oxide counterpart is that all the bands in the sulfide are squeezed towards the Fermi energy.




FIG. 3. Atomic projections of the spin decomposed total density of states (PDOS) for FeCr_2O_4 and FeCr_2S_4 . Fe and Cr contributions are from the 3d bands. O and S contributions are from the 2p and 3p orbitals respectively.

2. FeMn_2X_4

When the FeMn_2X_4 (thio)spinel is normal ($x = 0$), the Fe_A e and t_2 levels, which are very close or hybridized, appear in the maximum of the valence and minimum of the conduction bands in the minority and majority channel respectively, see Fig. 4 left panels. The half-metallic character of the normal FeMn_2X_4 (thio)spinel is also confirmed by the spin density analysis, showing a spin magnetization per formula unit of $M_S = 4.00 \mu_B$, see Table IV. At the Fermi energy, the spin up partially-occupied e_g band of Mn_B appears highly hybridized with the X p orbitals and with the Fe_A e and t_2 levels in the oxide and sulfide respectively, in agreement with the bigger atomic volume, enhancing orbital overlapping. The rest of the density of states is essentially the same as in the Cr-material, while in the Mn-based spinels the valence band is slightly shifted towards the Fermi energy and the Fe_A t_2 and e bands in the β channel of the spins appear more prominently. With the normal cation distribution, the bands of FeMn_2S_4 (Fig. 4 bottom-left panel), as in the case of FeCr_2S_4 , are shifted towards the Fermi energy, except for the Mn_B t_{2g} and e_g bands in the α channel of the spins.

When FeMn_2O_4 is a completely inverse spinel ($x = 1$), the system becomes half-semiconductor with a negligible band-gap, which has also been found experimentally,³⁵ see Fig. 4 top-right panel and also note in Table IV the integer $M_S = 4.00 \mu_B/\text{f.u.}$, typical of materials with band gaps. The partially-occupied and split $\text{Mn}_{\text{B1}} e_g$ bands appear close to the Fermi energy in the majority channel of the spins, where the t_{2g} level, with a small contribution from the e_g level, in the conduction band is highly hybridized with the O p orbitals. The $\text{Mn}_A t_2$ and e levels in the minority channel of the spins, are merged altogether and appear as a wide conduction band. In the inverse FeMn_2S_4 spinel, the bands are squeezed towards the Fermi energy, becoming a metal in both channels of the spins. The bands responsible for the conductivity properties are associated with the $\text{Mn}_{\text{B1}} e_g$ level and with the $\text{Fe}_{\text{B2}} t_{2g}$ level in the majority and minority channel of the spins respectively, see Fig. 4 bottom-right panel and the decimal $M_S = 4.02 \mu_B/\text{f.u.}$, typical of metals in Table IV. In general, we see that for any inversion degree, upon exchange of Cr by Mn cations, the bands responsible for the conduction properties are no longer the ones belonging to the atoms occupying the tetrahedral positions but those of $\text{Mn}_{\text{B}(1)}$.




FIG. 4. Atomic projections of the spin decomposed total density of states (PDOS) for FeMn_2O_4 and FeMn_2S_4 . Fe and Mn contributions are from the $3d$ bands. O and S contributions are from the $2p$ and $3p$ orbitals respectively.

3. $FeCo_2X_4$

When $FeCo_2O_4$ has a normal distribution, all the bands are pushed slightly towards the Fermi energy and especially those due to Co_B , see Fig. 5 top-left panel. As a result, the partially-occupied Co_B t_{2g} level that crosses the Fermi energy has a minimal band gap in the minority channel of the spins, making the normal $FeCo_2O_4$ spinel almost a half-metal, see also the integer value of the spin magnetization of saturation in Table IV. On the other hand, the sulfide counterpart has all the bands closer to the Fermi energy with symmetrical Co_B bands in the minority and majority spin channels (Fig. 5 bottom-left panel), due to the fully-occupied t_{2g} level which indicates non-magnetic behaviour for this atom (see Table IV). There is a peak at the Fermi energy, in the majority spin channel, with contributions from the partially-occupied Fe_A e and Co_B e_g levels. In the minority spin channel, the normal $FeCo_2S_4$ spinel is weakly conducting, as there is a small Co_B fully-occupied t_{2g} band strongly hybridized with S p orbitals that ends shortly after the Fermi energy in the conduction band side. Overall, the sulfide counterpart is metallic which is confirmed by a decimal spin magnetization of saturation, Table IV.

When the Co-based (thio)spinel have an inverse cation distribution, all the bands are slightly pushed away from the Fermi energy compared to the normal cation distribution, especially in the oxide, see Fig. 5 right panels. Fe_{B2} d bands appear in the typical range described so far for both oxide and sulfide spinels. For the oxide, Co_A valence d bands are in both spin channels, while in the α spin channel the partially-occupied t_2 level appears exclusively in the conduction part. The fully-occupied Co_{B1} valence t_{2g} levels are nearly symmetrically placed in both spin channels, rendering this atom as non-magnetic, see m_s in Table IV. The inverse cation distribution of the oxide has insulating properties, see also M_s in Table IV. Although the sulfide counterpart has the Co_A and Co_{B1} bands symmetrically placed in both channels of the spins, the bands crossing the Fermi energy give it metallic properties (see the decimal value of the spin magnetization of saturation $M_s = 2.46 \mu_B/f.u.$ in Table IV, typical of metals). These properties are due to the

hybridized partially-occupied $\text{Co}_A t_2$ and fully-occupied $\text{Co}_{B1} t_{2g}$ levels and to the merged $\text{Co}_A t_2$, $\text{Co}_{B1} t_{2g}$ and $\text{Fe}_{B2} t_{2g}$ levels in the majority and minority channel of spins, respectively.




FIG. 5. Atomic projections of the spin decomposed total density of states (PDOS) for FeCo_2O_4 and FeCo_2S_4 . Fe and Co contributions are from the $3d$ bands. O and S contributions are from the $2p$ and $3p$ orbitals respectively.

4. FeNi_2X_4

For both Ni-based (thio)spinels, when $x = 0$, the bands' pattern is similar and follows the same distribution as described in previous cases, see Fig. 6 left panels. The oxide is half-metal due to a strong hybridization of the partially-occupied $\text{Ni}_B e_g$ band with the O p orbitals that cross the Fermi energy in the majority channel of the spins, see also the integer value of M_S in Table IV. The main difference between oxide and sulfide lies in the fact that bands in the latter are closer to the Fermi energy in both spin channels, thus becoming a metallic system. The thiospinel's metallic character is given by the S p orbitals with a small hybridization (only in the majority channel of the spins) with the partially-occupied $\text{Fe}_A e$ and t_{2g} levels, see the decimal M_S in Table IV.

When Ni is filling the A sublattice, the Ni-based spinel becomes half-semiconductor with a band gap of 0.20 and 2.05 eV in the majority and minority channels of the spins, respectively, see Fig. 6 top right panel. While the position and distribution of the bands due to the ions occupying different positions is equivalent to what we have presented in previous cases, for inverse FeNi_2O_4 spinel, nonetheless, this is not the case for the sulfide counterpart. In the inverse FeNi_2S_4 system, the Ni_A and Ni_{B1} ions are less magnetic than expected and the valence and conduction bands are merged together, making this compound metallic for any inversion degree. The inverse Ni-based (thio)spinel have integer values of M_S (see Table IV) regardless of whether they are insulator or metal. Note that in the case of the metal inverse FeNi_2S_4 spinel, the decimal number in $M_S = 4.00 \mu_B/\text{f.u.}$ is a special case. In FeNi_2S_4 , for any inversion degree, the metallic character agrees with the experimental findings.^{21,103}




FIG. 6. Atomic projections of the spin decomposed total density of states (PDOS) for FeNi_2O_4 and FeNi_2S_4 . Fe and Ni contributions are from the 3d bands. O and S contributions are from the 2p and 3p orbitals respectively.

IV. SUMMARY AND CONCLUSIONS

We have performed systematic electronic structure calculations for a series of (thio)spinel, which elucidate the cation distribution as well as the magnetic and electronic properties of these materials.

We have determined the thermodynamic inversion degree for the FeM_2X_4 (thio)spinel at temperatures used typically in their synthesis, which agrees reasonably well with available experimental evidence. More quantitative results could be expected if additional values of inversion degrees and different cations arrangements to those explored in this work are considered for the spinel compositions, although we do not expect this to change the trend of our results. We have found that FeM_2X_4 spinels are more likely to have a normal distribution of cations when M is one of the two atoms to the left of Fe in the periodic table. FeMn_2O_4 has a metastable intermediate inversion degree that could only be found by considering entropic factors, which also agrees with experiment. It may be that the global minimum, *i.e.* the inverse spinel, is difficult to attain due to kinetic control. When M is one of the two atoms to the right of Fe in the periodic table, with the exception of FeCo_2O_4 , the spinels have an intermediate inversion degree ranging between 10 to 50%. Finally, the oxidic spinel of Co and Fe has a completely inverse distribution of the cations. The small equilibrium inversion degree of FeNi_2S_4 agrees acceptably well with the one found in natural samples. Fitting the experimental spin magnetization of saturation of FeNi_2X_4 to the ones calculated for the normal and inverse structures gives inversion degrees with a similar trend to those calculated using thermodynamic arguments. This procedure could also be applied to FeCo_2S_4 and FeNi_2O_4 if the magnetizations of saturation are known experimentally.

No single factor among those analyzed, *i.e.* neither crystal field stabilization effects nor the size of the cations, can account by themselves for the equilibrium inversion degree.

For the two extreme scenarios, namely the completely normal and inverse spinels, we have calculated the electronic and magnetic properties of the metal atoms as well as the electronic properties of the bulk phase. We found that the majority of the spinels for any extreme inversion degree are half-metals in the ferrimagnetic state. Notable exceptions are the inverse Co and Ni oxide spinels, which are insulators, and their sulfide counterparts that are metallic for any inversion degree, together with the inverse FeMn_2S_4 . Notably, we found that hard anions stretch the band structure, giving the biggest band gaps and therefore the best half-metallic properties.

Finally, we have proposed a theoretical structure for FeMn_2S_4 and FeCo_2S_4 and have predicted their electronic and magnetic properties and equilibrium inversion degree.

ACKNOWLEDGEMENTS

We acknowledge the Engineering & Physical Sciences Research Council (grants EP/G036675 and EP/K035355) for funding. *Via* our membership of the UK's HPC Materials Chemistry Consortium, which is funded by EPSRC (EP/L000202), this work made use of the facilities of HECToR and ARCHER, the UK's national high-performance computing services, which are funded by the Office of Science and Technology through EPSRC's High End Computing Programme. The authors also acknowledge the use of the UCL *Legion* High Performance Computing Facility (Legion@UCL), and associated support services, in the completion of this work. The authors would like to acknowledge that the work presented here made use of the IRIDIS High Performance Computing facility provided *via* the Centre for Innovation (Cfi), comprising the universities of Bristol, Oxford, Southampton and UCL in partnership with the STFC Rutherford Appleton Laboratory. DS-C thanks UCL for a Graduate Global Excellence Award and an Overseas Research Scholarship from the UCL Industrial Doctorate Centre in Molecular Modelling and Materials Science. AR is grateful to the Ramsay Memorial Trust and University College London for the provision of a Ramsay fellowship, and NHdL acknowledges the Royal Society for an Industry Fellowship.

- ¹ C. Felser, G.H. Fecher, and B. Balke, *Angew. Chemie Int. Ed.* **46**, 668 (2007).
- ² I. Žutić, J. Fabian, and S. Das Sarma, *Rev. Mod. Phys.* **76**, 323 (2004).
- ³ J.M.D. Coey and M. Venkatesan, *J. Appl. Phys.* **91**, 8345 (2002).
- ⁴ R.A. de Groot, F.M. Mueller, P.G. van Engen, and K.H.J. Buschow, *Phys. Rev. Lett.* **50**, 2024 (1983).
- ⁵ H. Sukegawa, Y. Miura, S. Muramoto, S. Mitani, T. Niizeki, T. Ohkubo, K. Abe, M. Shirai, K. Inomata, and K. Hono, *Phys. Rev. B* **86**, 184401 (2012).
- ⁶ T. Nozaki, H. Kubota, A. Fukushima, and S. Yuasa, *Appl. Phys. Express* **6**, 053005 (2013).
- ⁷ W. Eerenstein, T.T.M. Palstra, S.S. Saxena, and T. Hibma, *Phys. Rev. Lett.* **88**, 247204 (2002).
- ⁸ N. Berdunov, S. Murphy, G. Mariotto, and I. V. Shvets, *Phys. Rev. Lett.* **93**, 057201 (2004).
- ⁹ Z. Zhang and S. Satpathy, *Phys. Rev. B* **44**, 13319 (1991).
- ¹⁰ A. Roldan, D. Santos-Carballal, and N.H. de Leeuw, *J. Chem. Phys.* **138**, 204712 (2013).
- ¹¹ T. Kida, S. Honda, H. Itoh, J. Inoue, H. Yanagihara, E. Kita, and K. Mibu, *Phys. Rev. B* **84**, 104407 (2011).
- ¹² P. Piekarczyk, A.M. Oleś, and K. Parlinski, *Acta Phys. Pol. A* **118**, 307 (2010).
- ¹³ R.M. Cornell and U. Schwertmann, *The Iron Oxides*, Second Edition (Wiley-VCH Verlag GmbH & Co. KGaA, Weinheim, FRG, 2003), p. 664.
- ¹⁴ Z. Szotek, W.M. Temmerman, D. Ködderitzsch, A. Svane, L. Petit, and H. Winter, *Phys. Rev. B* **74**, 174431 (2006).
- ¹⁵ J.M.D. Coey and C.L. Chien, *MRS Bull.* **28**, 720 (2011).

- ¹⁶ L. Néel, *Ann. Phys. (Paris)*. **3**, 137 (1948).
- ¹⁷ R.D. Shannon, *Acta Crystallogr. Sect. A* **32**, 751 (1976).
- ¹⁸ P.I. Slick, in *Ferromagnetic Materials. A Handbook on the Properties of Magnetically Ordered Substances. Volume 2*, edited by E.P. Wohlfarth (North-Holland Publishing Company, Amsterdam, 1980), pp. 189 – 242.
- ¹⁹ V.A.M. Brabers, in *Handbook of Magnetic Materials. Volume 8*, edited by K.H.J. Buschow (Elsevier Science B.V., Amsterdam, 1995), pp. 189 – 324.
- ²⁰ D.J. Vaughan and J.A. Tossell, *Am. Mineral.* **66**, 1250 (1981).
- ²¹ D.J. Vaughan and J.R. Craig, *Am. Mineral.* **70**, 1036 (1985).
- ²² J. Charnock, C.D. Garner, R.A.D. Patrick, and D.J. Vaughan, *Am. Mineral.* **75**, 247 (1990).
- ²³ T.F.W. Barth and E. Posnjak, *Zeitschrift Für Krist. - Cryst. Mater.* **82**, 325 (1932).
- ²⁴ D.A. Andersson and C.R. Stanek, *Phys. Chem. Chem. Phys.* **15**, 15550 (2013).
- ²⁵ M. Robbins, G.K. Wertheim, R.C. Sherwood, and D.N.E. Buchanan, *Le J. Phys. Colloq.* **32**, C1 (1971).
- ²⁶ V. Kocsis, S. Bordács, D. Varjas, K. Penc, A. Abouelsayed, C.A. Kuntscher, K. Ohgushi, Y. Tokura, and I. Kézsmárki, *Phys. Rev. B* **87**, 064416 (2013).
- ²⁷ S. Bordács, D. Varjas, I. Kézsmárki, G. Mihály, L. Baldassarre, A. Abouelsayed, C.A. Kuntscher, K. Ohgushi, and Y. Tokura, *Phys. Rev. Lett.* **103**, 077205 (2009).
- ²⁸ S. Klemme, H.S.C. O'Neill, W. Schnelle, and E. Gmelin, *Am. Mineral.* **85**, 1686 (2000).
- ²⁹ G.L. Bacchella and M. Pinot, *Le J. Phys.* **25**, 537 (1964).

- ³⁰ J. Van Landuyt, R. De Ridder, V.A.M. Brabers, and S. Amelinckx, *Mater. Res. Bull.* **7**, 327 (1972).
- ³¹ K. Ohgushi, Y. Okimoto, T. Ogasawara, S. Miyasaka, and Y. Tokura, *J. Phys. Soc. Japan* **77**, 034713 (2008).
- ³² M.S. Park, S.K. Kwon, S.J. Youn, and B.I. Min, *Phys. Rev. B* **59**, 10018 (1999).
- ³³ G. Shirane, D.E. Cox, and S.J. Pickart, *J. Appl. Phys.* **35**, 954 (1964).
- ³⁴ A.P. Ramirez, R.J. Cava, and J. Krajewski, *Nature* **386**, 156 (1997).
- ³⁵ J.A. Kulkarni and V.S. Darshane, *Thermochim. Acta* **93**, 473 (1985).
- ³⁶ A.P.B. Sinha, N.R. Sanjana, and A.B. Biswas, *Acta Crystallogr.* **10**, 439 (1957).
- ³⁷ B. Boucher, R. Buhl, and M. Perrin, *J. Appl. Phys.* **40**, 1126 (1969).
- ³⁸ R. Buhl, *J. Phys. Chem. Solids* **30**, 805 (1969).
- ³⁹ S.R. Liu, D.H. Ji, J. Xu, Z.Z. Li, G.D. Tang, R.R. Bian, W.H. Qi, Z.F. Shang, and X.Y. Zhang, *J. Alloys Compd.* **581**, 616 (2013).
- ⁴⁰ T.A.S. Ferreira, J.C. Waerenborgh, M.H.R.M. Mendonça, M.R. Nunes, and F.M. Costa, *Solid State Sci.* **5**, 383 (2003).
- ⁴¹ H. Le Trong, A. Barnabé, L. Presmanes, and P. Tailhades, *Solid State Sci.* **10**, 550 (2008).
- ⁴² I.P. Muthuselvam and R.N. Bhowmik, *Solid State Sci.* **11**, 719 (2009).
- ⁴³ M.W. Shafer, *J. Appl. Phys.* **33**, 1210 (1962).
- ⁴⁴ S. Haider, R. Grau-Crespo, A.J. Devey, and N.H. de Leeuw, *Geochim. Cosmochim. Acta* **88**, 275 (2012).

- ⁴⁵ C. Tenailleau, B. Etschmann, R.M. Ibberson, and A. Pring, *Am. Mineral.* **91**, 1442 (2006).
- ⁴⁶ P. Waldner, *J. Chem. Thermodyn.* **41**, 171 (2009).
- ⁴⁷ B. Balke, S. Wurmehl, G.H. Fecher, C. Felser, and J. Kübler, *Sci. Technol. Adv. Mater.* **9**, 014102 (2008).
- ⁴⁸ I. Galanakis, P.H. Dederichs, and N. Papanikolaou, *Phys. Rev. B* **66**, 134428 (2002).
- ⁴⁹ G. Kresse and J. Hafner, *Phys. Rev. B* **47**, 558 (1993).
- ⁵⁰ G. Kresse and J. Hafner, *Phys. Rev. B* **49**, 14251 (1994).
- ⁵¹ G. Kresse and J. Furthmüller, *Comput. Mater. Sci.* **6**, 15 (1996).
- ⁵² G. Kresse and J. Furthmüller, *Phys. Rev. B* **54**, 11169 (1996).
- ⁵³ J.P. Perdew, A. Ruzsinszky, G.I. Csonka, O.A. Vydrov, G.E. Scuseria, L.A. Constantin, X. Zhou, and K. Burke, *Phys. Rev. Lett.* **100**, 136406 (2008).
- ⁵⁴ M. De La Pierre, R. Orlando, L. Maschio, K. Doll, P. Ugliengo, and R. Dovesi, *J. Comput. Chem.* **32**, 1775 (2011).
- ⁵⁵ S. Grimme, *J. Comput. Chem.* **27**, 1787 (2006).
- ⁵⁶ D. Santos-Carballal, A. Roldan, R. Grau-Crespo, and N.H. de Leeuw, *Phys. Chem. Chem. Phys.* **16**, 21082 (2014).
- ⁵⁷ S.S. Tafreshi, A. Roldan, N.Y. Dzade, and N.H. de Leeuw, *Surf. Sci.* **622**, 1 (2014).
- ⁵⁸ S. Irrera, A. Roldan, G. Portalone, and N.H. De Leeuw, *J. Phys. Chem. C* **117**, 3949 (2013).
- ⁵⁹ S. Haider, A. Roldan, and N.H. de Leeuw, *J. Phys. Chem. C* **118**, 1958 (2014).
- ⁶⁰ N.Y. Dzade, A. Roldan, and N.H. de Leeuw, *Phys. Chem. Chem. Phys.* **16**, 15444 (2014).

- ⁶¹ N.Y. Dzade, A. Roldan, and N.H. de Leeuw, *J. Chem. Phys.* **139**, 124708 (2013).
- ⁶² G. Kresse and D. Joubert, *Phys. Rev. B* **59**, 1758 (1999).
- ⁶³ P.E. Blöchl, *Phys. Rev. B* **50**, 17953 (1994).
- ⁶⁴ A. Baldereschi, *Phys. Rev. B* **7**, 5212 (1973).
- ⁶⁵ D.J. Chadi and M.L. Cohen, *Phys. Rev. B* **8**, 5747 (1973).
- ⁶⁶ H.J. Monkhorst and J.D. Pack, *Phys. Rev. B* **13**, 5188 (1976).
- ⁶⁷ R.F.W. Bader, *Atoms in Molecules: A Quantum Theory* (Oxford University Press, Oxford (UK), 1990).
- ⁶⁸ G. Henkelman, A. Arnaldsson, and H. Jónsson, *Comput. Mater. Sci.* **36**, 354 (2006).
- ⁶⁹ E. Sanville, S.D. Kenny, R. Smith, and G. Henkelman, *J. Comput. Chem.* **28**, 899 (2007).
- ⁷⁰ W. Tang, E. Sanville, and G. Henkelman, *J. Phys. Condens. Matter* **21**, 084204 (2009).
- ⁷¹ S.L. Dudarev, G.A. Botton, S.Y. Savrasov, C.J. Humphreys, and A.P. Sutton, *Phys. Rev. B* **57**, 1505 (1998).
- ⁷² V.I. Anisimov, M.A. Korotin, J. Zaanen, and O.K. Andersen, *Phys. Rev. Lett.* **68**, 345 (1992).
- ⁷³ J. Heyd, G.E. Scuseria, and M. Ernzerhof, *J. Chem. Phys.* **118**, 8207 (2003).
- ⁷⁴ J. Heyd, G.E. Scuseria, and M. Ernzerhof, *J. Chem. Phys.* **124**, 219906 (2006).
- ⁷⁵ J. Heyd and G.E. Scuseria, *J. Chem. Phys.* **120**, 7274 (2004).
- ⁷⁶ J. Heyd and G.E. Scuseria, *J. Chem. Phys.* **121**, 1187 (2004).
- ⁷⁷ J. Heyd, J.E. Peralta, G.E. Scuseria, and R.L. Martin, *J. Chem. Phys.* **123**, 174101 (2005).
- ⁷⁸ J.E. Peralta, J. Heyd, G.E. Scuseria, and R.L. Martin, *Phys. Rev. B* **74**, 073101 (2006).

⁷⁹ A. V. Krukau, O.A. Vydrov, A.F. Izmaylov, and G.E. Scuseria, *J. Chem. Phys.* **125**, 224106 (2006).

⁸⁰ T.M. Henderson, J. Paier, and G.E. Scuseria, *Phys. Status Solidi B* **248**, 767 (2011).

⁸¹ J.P. Perdew, K. Burke, and M. Ernzerhof, *Phys. Rev. Lett.* **77**, 3865 (1996).

⁸² J.P. Perdew, K. Burke, and M. Ernzerhof, *Phys. Rev. Lett.* **78**, 1396 (1997).

⁸³ J.P. Perdew, M. Ernzerhof, and K. Burke, *J. Chem. Phys.* **105**, 9982 (1996).

⁸⁴ A.J. Devey, R. Grau-Crespo, and N.H. de Leeuw, *Phys. Rev. B* **79**, 195126 (2009).

⁸⁵ L. Wang, T. Maxisch, and G. Ceder, *Phys. Rev. B* **73**, 195107 (2006).

⁸⁶ A. Rohrbach, J. Hafner, and G. Kresse, *J. Phys. Condens. Matter* **15**, 979 (2003).

⁸⁷ D. Fritsch and C. Ederer, *Phys. Rev. B* **82**, 104117 (2010).

⁸⁸ Y. Seminovski, P. Palacios, P. Wahnón, and R. Grau-Crespo, *Appl. Phys. Lett.* **100**, 102112 (2012).

⁸⁹ S.-H. Wei and S. Zhang, *Phys. Rev. B* **63**, 045112 (2001).

⁹⁰ A. Walsh, S.-H. Wei, Y. Yan, M.M. Al-Jassim, J.A. Turner, M. Woodhouse, and B.A. Parkinson, *Phys. Rev. B* **76**, 165119 (2007).

⁹¹ D. Fritsch and C. Ederer, *J. Phys. Conf. Ser.* **292**, 012014 (2011).

⁹² D. Fritsch and C. Ederer, *Appl. Phys. Lett.* **99**, 081916 (2011).

⁹³ V. Montoro, *Gazz. Chim. Ital.* **68**, 728 (1938).

⁹⁴ J.P. Wright, J.P. Attfield, and P.G. Radaelli, *Phys. Rev. B* **66**, 214422 (2002).

⁹⁵ B.J. Skinner, R.C. Erd, and F.S. Grimaldi, *Am. Mineral.* **49**, 543 (1964).

- ⁹⁶ A. Navrotsky and O.J. Kleppa, *J. Inorg. Nucl. Chem.* **29**, 2701 (1967).
- ⁹⁷ A. Seko, F. Oba, and I. Tanaka, *Phys. Rev. B* **81**, 054114 (2010).
- ⁹⁸ P.F. Ndione, Y. Shi, V. Stevanovic, S. Lany, A. Zakutayev, P.A. Parilla, J.D. Perkins, J.J. Berry, D.S. Ginley, and M.F. Toney, *Adv. Funct. Mater.* **24**, 610 (2014).
- ⁹⁹ E.J. Palin, A.M. Walker, and R.J. Harrison, *Am. Mineral.* **93**, 1363 (2008).
- ¹⁰⁰ F. Tielens, M. Calatayud, R. Franco, J.M. Recio, J. Pérez-Ramírez, and C. Minot, *J. Phys. Chem. B* **110**, 988 (2006).
- ¹⁰¹ C.J. Kriessman and S.E. Harrison, *Phys. Rev.* **103**, 857 (1956).
- ¹⁰² H.S.C. O'Neill and A. Navrotsky, *Am. Mineral.* **68**, 181 (1983).
- ¹⁰³ M.G. Townsend, J.R. Gosselin, J.L. Horwood, L.G. Ripley, and R.J. Tremblay, *Phys. Status Solidi* **40**, K25 (1977).
- ¹⁰⁴ J.R. Craig, *Am. Mineral.* **56**, 1303 (1971).
- ¹⁰⁵ P.A. Smith, C.D. Spencer, and R.P. Stillwell, *J. Phys. Chem. Solids* **39**, 107 (1978).
- ¹⁰⁶ M. Takahashi and M.E. Fine, *J. Appl. Phys.* **43**, 4205 (1972).
- ¹⁰⁷ P.J. Murray and J.W. Linnett, *J. Phys. Chem. Solids* **37**, 1041 (1976).
- ¹⁰⁸ F.K. Lotgering, *Phil. Res. Rep.* **11**, 337 (1956), cited by T.A.S. Ferreira, J.C. Waerenborgh, M.H.R.M. Mendonça, M.R. Nunes, and F.M. Costa, *Solid State Sci.* **5**, 383 (2003); P.A. Smith, C.D. Spencer, and R.P. Stillwell, *J. Phys. Chem. Solids* **39**, 107 (1978); and M. Takahashi and M.E. Fine, *J. Appl. Phys.* **43**, 4205 (1972).
- ¹⁰⁹ G. Blasse, *Phil. Res. Rep.* **18**, 383 (1963), cited by T.A.S. Ferreira, J.C. Waerenborgh, M.H.R.M. Mendonça, M.R. Nunes, and F.M. Costa, *Solid State Sci.* **5**, 383 (2003); P.A. Smith, C.D. Spencer,

and R.P. Stillwell, *J. Phys. Chem. Solids* **39**, 107 (1978); and M. Takahashi and M.E. Fine, *J. Appl. Phys.* **43**, 4205 (1972).

¹¹⁰ L. Cemič and O.J. Kleppa, *Phys. Chem. Miner.* **14**, 52 (1987).

¹¹¹ R.J. Hill, J.R. Craig, and G. V. Gibbs, *Phys. Chem. Miner.* **4**, 317 (1979).

¹¹² D.S. McClure, *J. Phys. Chem. Solids* **3**, 311 (1957).

¹¹³ J.D. Dunitz and L.E. Orgel, *J. Phys. Chem. Solids* **3**, 318 (1957).

¹¹⁴ A.N. Cormack, G.V. Lewis, S.C. Parker, and C.R.A. Catlow, *J. Phys. Chem. Solids* **49**, 53 (1988).

¹¹⁵ S. Kawano, N. Achiwa, N. Yamamoto, and S. Higashi, *Mater. Res. Bull.* **11**, 911 (1976).

¹¹⁶ J.M.D. Coey, M. Venkatesan, and M.A. Bari, in *High Magnetic Fields. Lecture Notes in Physics, Vol. 595*, edited by C. Berthier, L.P. Levy, and G. Martinez (Springer Berlin Heidelberg, 2001), pp. 377–396.

¹¹⁷ J.M.D. Coey and S. Sanvito, *J. Phys. D. Appl. Phys.* **37**, 988 (2004).